



**Product Data Sheet &
General Processing Conditions**

**RTP 399 X 115062 G
Polycarbonate (PC)
Carbon Nanotube
Electrically Conductive
ESD Protection**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.21	1.21	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0060 - 0.0080 in/in	0.60 - 0.80 %	D 955
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	18.0 ft-lbs/in	961 J/m	D 4812
Tensile Strength	9100 psi	63 MPa	D 638
Tensile Elongation	4.0 - 7.0 %	4.0 - 7.0 %	D 638
Tensile Modulus	0.40 x 10 ⁶ psi	2758 MPa	D 638
Flexural Strength	15600 psi	108 MPa	D 790
Flexural Modulus	0.42 x 10 ⁶ psi	2896 MPa	D 790
ELECTRICAL			
Volume Resistivity	< 1E2 ohm.cm	< 1E2 ohm.cm	D 257
Surface Resistivity	< 1E5 ohm/sq	< 1E5 ohm/sq	D 257
Surface Resistance	< 1E4 ohm	< 1E4 ohm	ESD STM11.11
Static Decay MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 0.50 s	< 0.50 s	FTMS101C 4046.1

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	550 - 600 °F	288 - 316 °C
Mold Temperature	180 - 250 °F	82 - 121 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Desiccant Type Dryer Required.