



**Product Data Sheet &
General Processing Conditions**

**PermaStat® 2500
Polycarbonate/ABS Alloy (PC/ABS)
ESD Protection
Permanently Anti-static**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.15	1.15	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0060 - 0.0080 in/in	0.60 - 0.80 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	18.0 ft-lbs/in	961 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	5500 psi	38 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.25 x 10 ⁶ psi	1724 MPa	D 638
Flexural Strength	8000 psi	55 MPa	D 790
Flexural Modulus	0.25 x 10 ⁶ psi	1724 MPa	D 790

ELECTRICAL

Volume Resistivity	1E+09 - 9.9E+10 ohm.cm	1E+09 - 9.9E+10 ohm.cm	D 257
Surface Resistivity	1E+10 - 9.9E+11 ohm/sq	1E+10 - 9.9E+11 ohm/sq	D 257
Surface Resistance	1E+09 - 9.9E+10 ohm	1E+09 - 9.9E+10 ohm	ESD STM11.11
Static Decay MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 2.00 s	< 2.00 s	FTMS101C 4046.1

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	420 - 480 °F	216 - 249 °C
Mold Temperature	125 - 200 °F	52 - 93 °C
Drying	4 hrs @ 200 °F	4 hrs @ 93 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Do not exceed 520 °F (270 °C) melt temperature.
Desiccant Type Dryer Required.