



**Product Data Sheet &
General Processing Conditions**

**RTP 2500 FR A
Polycarbonate/ABS Alloy (PC/ABS)
Flame Retardant
UL94 V-0**



PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.20	1.20	D 792
Melt Flow Rate			
@ 260 °C, / 1.2 kg	3.00 - 6.00 g/10 min	3.00 - 6.00 g/10 min	D 1238
Molding Shrinkage			
1/8 in (3.2 mm) section	0.0045 - 0.0075 in/in	0.45 - 0.75 %	D 955

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	12.0 ft-lbs/in	641 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	9500 psi	66 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.40 x 10 ⁶ psi	2758 MPa	D 638
Flexural Strength	15000 psi	103 MPa	D 790
Flexural Modulus	0.42 x 10 ⁶ psi	2896 MPa	D 790

ELECTRICAL

Dielectric Strength, S/T, in oil	870 VPM	34.3 kV/mm	D 149
Volume Resistivity	> 1E16 ohm.cm	> 1E16 ohm.cm	D 257

THERMAL

Deflection Temperature			
@ 264 psi (1820 kPa)	210 °F	99 °C	D 648
Ignition Resistance*			
Flammability	V-0 @ 1/16 in	V-0 @ 1.5 mm	UL94
Flammability	5VA @ 1/8 in	5VA @ 3.0 mm	UL94

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	470 - 525 °F	243 - 274 °C
Mold Temperature	125 - 200 °F	52 - 93 °C
Drying	4 hrs @ 200 °F	4 hrs @ 93 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Desiccant Type Dryer Required.