



**Product Data Sheet &
General Processing Conditions**

RTP 2099 X 134682
Polycarbonate/PBT Alloy
Permanently Static Dissipative
ESD Protection
Impact Modified
UV Stabilized



This compound has been formulated to meet the static dissipative requirements of the ATEX Directive.

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.17	1.17	D 792
Melt Flow Rate			
@ 230 °C, / 3.8 kg	5.00 - 8.00 g/10 min	5.00 - 8.00 g/10 min	D 1238
Molding Shrinkage			
1/8 in (3.2 mm) section	0.0060 - 0.0080 in/in	0.60 - 0.80 %	D 955

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	14.0 ft-lbs/in	747 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	6000 psi	41 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.24 x 10 ⁶ psi	1655 MPa	D 638
Flexural Strength	9500 psi	66 MPa	D 790
Flexural Modulus	0.25 x 10 ⁶ psi	1724 MPa	D 790

ELECTRICAL

Surface Resistance*	< 1E9 ohm	< 1E9 ohm	IEC 60079:0
Static Decay			
MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 0.50 s	< 0.50 s	FTMS101C 4046.1

THERMAL

Deflection Temperature			
@ 264 psi (1820 kPa)	183 °F	84 °C	D 648
@ 66 psi (455 kPa)	205 °F	96 °C	D 648
Ignition Resistance*			
Flammability	HB @ 1/32 in	HB @ 0.8 mm	UL94

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

*ATEX Directive mandates surface resistance limits of <1.0E+09 ohm at 50% RH or <1.0E+11 ohm at 30% RH.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	410 - 480 °F	210 - 249 °C
Mold Temperature	150 - 230 °F	66 - 110 °C
Drying	4 hrs @ 180 °F	4 hrs @ 82 °C
Moisture Content	< 0.02 %	< 0.02 %