

(+) 18816996168

Poncioplastics.com



**Product Data Sheet &
General Processing Conditions**

**RTP 2211 HF
Polyetheretherketone (PEEK)
Glass Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	60 %	60 %	
Specific Gravity	1.84	1.84	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0010 - 0.0030 in/in	0.10 - 0.30 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	2.5 ft-lbs/in	133 J/m	D 256
unnotched 1/8 in (3.2 mm) section	14.0 ft-lbs/in	747 J/m	D 4812
Tensile Strength	31000 psi	214 MPa	D 638
Tensile Elongation	1.0 - 2.0 %	1.0 - 2.0 %	D 638
Tensile Modulus	3.70 x 10 ⁶ psi	25512 MPa	D 638
Flexural Strength	45000 psi	310 MPa	D 790
Flexural Modulus	3.50 x 10 ⁶ psi	24132 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	> 572 °F	> 300 °C	D 648
Ignition Resistance* Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	12000 - 18000 psi	83 - 124 MPa
Melt Temperature	660 - 750 °F	349 - 399 °C
Mold Temperature	325 - 425 °F	163 - 218 °C
Drying	3 hrs @ 300 °F	3 hrs @ 149 °C
Moisture Content	0.10 %	0.10 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Desiccant Type Dryer Required.