

(+) 18816996168

Ponciplastics.com



Product Data Sheet & General Processing Conditions

RTP 2205 HF Polyetheretherketone (PEEK) Glass Fiber High Flow

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	30 %	30 %	
Specific Gravity	1.52	1.52	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0030 in/in	0.30 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	2.0 ft-lbs/in	107 J/m	D 256
unnotched 1/8 in (3.2 mm) section	20.0 ft-lbs/in	1068 J/m	D 4812
Tensile Strength	27000 psi	186 MPa	D 638
Tensile Elongation	3.0 %	3.0 %	D 638
Tensile Modulus	1.70 x 10 ⁶ psi	11722 MPa	D 638
Flexural Strength	41000 psi	283 MPa	D 790
Flexural Modulus	1.61 x 10 ⁶ psi	11101 MPa	D 790

ELECTRICAL

Dielectric Strength, S/T, in oil	500 VPM	19.7 kV/mm	D 149
Dielectric Constant, 1 MHz, Dry	3.4	3.4	D 150
Dissipation Factor, 1 MHz, Dry	< 0.0100	< 0.0100	D 150
Volume Resistivity	> 1E15 ohm.cm	> 1E15 ohm.cm	D 257

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	600 °F	316 °C	D 648
Ignition Resistance* Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801
Coefficient of Linear Thermal Expansion Flow Direction	0.2 x 10 ⁻⁵ /°F	0.3 x 10 ⁻⁵ /°C	E 831
Transverse Direction	2.8 x 10 ⁻⁵ /°F	5.0 x 10 ⁻⁵ /°C	E 831

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	12000 - 18000 psi	83 - 124 MPa
Melt Temperature	660 - 750 °F	349 - 399 °C
Mold Temperature	325 - 425 °F	163 - 218 °C
Drying	3 hrs @ 300 °F	3 hrs @ 149 °C
Moisture Content	0.10 %	0.10 %
Dew Point	-20 °F	-29 °C