

(+) 18816996168

Poncioplastics.com



**Product Data Sheet &
General Processing Conditions**

**RTP 4107
Polyetherketoneketone (PEKK)
Glass Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	40 %	40 %	
Specific Gravity	1.60	1.60	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0020 in/in	0.20 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	2.0 ft-lbs/in	107 J/m	D 256
unnotched 1/8 in (3.2 mm) section	17.0 ft-lbs/in	908 J/m	D 4812
Tensile Strength	27500 psi	190 MPa	D 638
Tensile Elongation	1.9 %	1.9 %	D 638
Tensile Modulus	2.00 x 10 ⁶ psi	13790 MPa	D 638
Flexural Strength	40000 psi	276 MPa	D 790
Flexural Modulus	1.80 x 10 ⁶ psi	12411 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	> 600 °F	> 316 °C	D 648
Ignition Resistance* Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	15000 - 20000 psi	103 - 138 MPa
Melt Temperature	710 - 720 °F	377 - 382 °C
Mold Temperature	300 - 450 °F	149 - 232 °C
Drying	3 hrs @ 300 °F	3 hrs @ 149 °C
Moisture Content	0.10 %	0.10 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Desiccant Type Dryer Required.