

(+) 18816996168

Poncioplastics.com



**Product Data Sheet &
General Processing Conditions**

**RTP 2099 X 124789 C
Bio-Based Polylactic Acid (PLA)
Impact Modified
Transparent
84% Renewable Resource Content**

Not optically transparent. Thick wall sections can be hazy.

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.22	1.22	D 792
MECHANICAL			
Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	1.5 ft-lbs/in	80 J/m	D 256
unnotched 1/8 in (3.2 mm) section	25.0 ft-lbs/in	1335 J/m	D 4812
Tensile Strength	7000 psi	48 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.41 x 10 ⁶ psi	2827 MPa	D 638
Flexural Strength	10000 psi	69 MPa	D 790
Flexural Modulus	0.41 x 10 ⁶ psi	2827 MPa	D 790
THERMAL			
Deflection Temperature @ 66 psi (455 kPa)	124 °F	51 °C	D 648

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	8000 - 15000 psi	55 - 103 MPa
Melt Temperature	340 - 370 °F	171 - 188 °C
Mold Temperature	50 - 75 °F	10 - 24 °C
Drying	2 - 6 hrs @ 120 °F	2 - 6 hrs @ 49 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-40 °F	-40 °C