



**Product Data Sheet &
General Processing Conditions**

**RTP 4799 X 115376 F
Polytrimethylene Terephthalate (PTT)
Biobased Polyester
Glass Fiber
PTFE Lubricated
20% Bio-Content**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.69	1.69	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0030 in/in	0.30 %	D 955

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	1.5 ft-lbs/in	80 J/m	D 256
unnotched 1/8 in (3.2 mm) section	12.0 ft-lbs/in	641 J/m	D 4812
Tensile Strength	18000 psi	124 MPa	D 638
Tensile Elongation	3.0 %	3.0 %	D 638
Flexural Strength	28000 psi	193 MPa	D 790
Flexural Modulus	1.40 x 10 ⁶ psi	9653 MPa	D 790

THERMAL

Deflection Temperature			
@ 264 psi (1820 kPa)	400 °F	204 °C	D 648
@ 66 psi (455 kPa)	425 °F	218 °C	D 648
Ignition Resistance*			
Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	450 - 500 °F	232 - 260 °C
Mold Temperature	190 - 250 °F	88 - 121 °C
Drying	4 - 6 hrs @ 260 °F	4 - 6 hrs @ 127 °C
Moisture Content	0.01 %	0.01 %
Dew Point	-40 °F	-40 °C

PROCESSING NOTES

Desiccant Type Dryer Required.