

(+) 18816996168

Poncioplastics.com



**Product Data Sheet &
General Processing Conditions**

**PermaStat® 100 HI
Polypropylene (PP)
High Impact
ESD Protection
Permanently Anti-static**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.92	0.92	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0100 - 0.0200 in/in	1.00 - 2.00 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	15.0 ft-lbs/in	801 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	2700 psi	19 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.15 x 10 ⁶ psi	1034 MPa	D 638
Flexural Strength	3700 psi	26 MPa	D 790
Flexural Modulus	0.13 x 10 ⁶ psi	896 MPa	D 790

ELECTRICAL

Volume Resistivity	1E9 - 9.9E10 ohm.cm	1E9 - 9.9E10 ohm.cm	D 257
Surface Resistivity	1E10 - 9.9E11 ohm/sq	1E10 - 9.9E11 ohm/sq	D 257
Surface Resistance	1E9 - 9.9E10 ohm	1E9 - 9.9E10 ohm	ESD STM11.11
Static Decay MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 2.00 s	< 2.00 s	FTMS101C 4046.1

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	7000 - 11000 psi	48 - 76 MPa
Melt Temperature	340 - 400 °F	171 - 204 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C
Moisture Content	0.10 %	0.10 %

PROCESSING NOTES

Do not exceed 520 °F (270 °C) melt temperature.