

(+) 18816996168

Ponciplastics.com



Product Data Sheet & General Processing Conditions

RTP 100 HI Polypropylene (PP) High Impact

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.91	0.91	D 792
Melt Flow Rate @ 230 °C, / 2.16 kg	4.00 g/10 min	4.00 g/10 min	D 1238
Molding Shrinkage 1/8 in (3.2 mm) section	0.0150 - 0.0200 in/in	1.50 - 2.00 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	14.0 ft-lbs/in	747 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	3100 psi	21 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.15 x 10 ⁶ psi	1034 MPa	D 638
Flexural Strength	4000 psi	28 MPa	D 790
Flexural Modulus	0.13 x 10 ⁶ psi	896 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	110 °F	43 °C	D 648
@ 66 psi (455 kPa)	175 °F	79 °C	D 648
Ignition Resistance*			
Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C