



**Product Data Sheet &
General Processing Conditions**

**RTP 100
Polypropylene (PP)
Unfilled**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.91	0.91	D 792
Melt Flow Rate @ 230 °C, / 2.16 kg	4.00 g/10 min	4.00 g/10 min	D 1238
Molding Shrinkage 1/8 in (3.2 mm) section	0.0150 - 0.0200 in/in	1.50 - 2.00 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	30.0 ft-lbs/in	1602 J/m	D 4812
Tensile Strength	4700 psi	32 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.25 x 10 ⁶ psi	1724 MPa	D 638
Flexural Strength	6000 psi	41 MPa	D 790
Flexural Modulus	0.20 x 10 ⁶ psi	1379 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	130 °F	54 °C	D 648
@ 66 psi (455 kPa)	225 °F	107 °C	D 648
Ignition Resistance*			
Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C