



Product Data Sheet & General Processing Conditions

RTP 103 CC Polypropylene (PP) Glass Fiber Chemically Coupled

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	20 %	20 %	
Specific Gravity	1.04	1.04	D 792
Melt Flow Rate			
@ 230 °C, / 2.16 kg	3.50 g/10 min	3.50 g/10 min	D 1238
Molding Shrinkage			
1/8 in (3.2 mm) section	0.0020 - 0.0050 in/in	0.20 - 0.50 %	D 955

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	1.8 ft-lbs/in	93 J/m	D 256
unnotched 1/8 in (3.2 mm) section	10.5 ft-lbs/in	561 J/m	D 4812
Tensile Strength	8500 psi	59 MPa	D 638
Tensile Elongation	6.0 - 7.0 %	6.0 - 7.0 %	D 638
Tensile Modulus	0.55 x 10 ⁶ psi	3792 MPa	D 638
Flexural Strength	12500 psi	86 MPa	D 790
Flexural Modulus	0.45 x 10 ⁶ psi	3103 MPa	D 790

ELECTRICAL

Dielectric Constant, 1 MHz, Dry	2.4	2.4	D 150
Dissipation Factor, 1 MHz, Dry	< 0.0020	< 0.0020	D 150

THERMAL

Deflection Temperature			
@ 264 psi (1820 kPa)	265 °F	129 °C	D 648
@ 66 psi (455 kPa)	305 °F	152 °C	D 648
Ignition Resistance*			
Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C
Moisture Content	< 0.20 %	< 0.20 %