

(+) 18816996168

Ponciplastics.com



Product Data Sheet & General Processing Conditions

RTP 105 CC HI Polypropylene (PP) High Impact Glass Fiber Chemically Coupled

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	30 %	30 %	
Specific Gravity	1.12	1.12	D 792
Melt Flow Rate @ 230 °C, / 2.16 kg	2.00 g/10 min	2.00 g/10 min	D 1238
Molding Shrinkage 1/8 in (3.2 mm) section	0.0010 - 0.0040 in/in	0.10 - 0.40 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	5.0 ft-lbs/in	267 J/m	D 256
unnotched 1/8 in (3.2 mm) section	15.0 ft-lbs/in	801 J/m	D 4812
Tensile Strength	7500 psi	52 MPa	D 638
Tensile Elongation	6.0 - 7.0 %	6.0 - 7.0 %	D 638
Tensile Modulus	0.80 x 10 ⁶ psi	5516 MPa	D 638
Flexural Strength	12000 psi	83 MPa	D 790
Flexural Modulus	0.55 x 10 ⁶ psi	3792 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	260 °F	127 °C	D 648
@ 66 psi (455 kPa)	310 °F	154 °C	D 648
Ignition Resistance*			
Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C