



**Product Data Sheet &
General Processing Conditions**

**RTP 152 HI
Polypropylene (PP)
Copolymer
Flame Retardant**

The RTP 152 family of compounds are flame retarded, unreinforced polypropylene materials. They offer excellent moldability, non-corrosive characteristics and the living-hinge effect.

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.93	0.93	D 792
Melt Flow Rate @ 230 °C, / 2.16 kg	3.00 - 5.00 g/10 min	3.00 - 5.00 g/10 min	D 1238
Molding Shrinkage 1/8 in (3.2 mm) section	0.0150 - 0.0200 in/in	1.50 - 2.00 %	D 955
Water Absorption, 24 hrs @ 23°C	0.010 %	0.010 %	D 570

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	12.0 ft-lbs/in	641 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	2800 psi	19 MPa	D 638
Tensile Elongation Break	> 100.0 %	> 100.0 %	D 638
Tensile Modulus	0.14 x 10 ⁶ psi	965 MPa	D 638
Flexural Strength	3300 psi	23 MPa	D 790
Flexural Modulus	0.12 x 10 ⁶ psi	827 MPa	D 790

ELECTRICAL

Volume Resistivity	> 1E15 ohm.cm	> 1E15 ohm.cm	D 257
--------------------	---------------	---------------	-------

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	110 °F	43 °C	D 648
Ignition Resistance* Flammability**	V-2 @ 1/32 in	V-2 @ 0.8 mm	D 3801

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C