



**Product Data Sheet &
General Processing Conditions**

RTP 155 A
Polypropylene (PP)
Mineral
Flame Retardant
Non-PBB/PBDE
UL94 V-0


PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	20 %	20 %	
Specific Gravity	1.37	1.37	D 792
Melt Flow Rate			
@ 230 °C, / 2.16 kg	4.00 - 6.00 g/10 min	4.00 - 6.00 g/10 min	D 1238
Molding Shrinkage			
1/8 in (3.2 mm) section	0.0070 - 0.0100 in/in	0.70 - 1.00 %	D 955
Water Absorption, 24 hrs @ 23°C	0.030 %	0.030 %	D 570

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	12.0 ft-lbs/in	641 J/m	D 4812
Tensile Strength	3000 psi	21 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.32 x 10 ⁶ psi	2206 MPa	D 638
Flexural Strength	5500 psi	38 MPa	D 790
Flexural Modulus	0.35 x 10 ⁶ psi	2413 MPa	D 790

THERMAL

Deflection Temperature			
@ 264 psi (1820 kPa)	158 °F	70 °C	D 648
@ 66 psi (455 kPa)	257 °F	125 °C	D 648
Ignition Resistance*			
Flammability	V-0 @ 1/16 in	V-0 @ 1.5 mm	UL94
Flammability	5VA @ 1/8 in	5VA @ 3.0 mm	UL94

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C