

(+) 18816996168

Ponciplastics.com



Product Data Sheet & General Processing Conditions

RTP PP FR2 Polypropylene (PP) Value Product Flame Retardant

Flame Retardant - Value Product

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.93	0.93	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0150 - 0.0200 in/in	1.50 - 2.00 %	D 955
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.7 ft-lbs/in	37 J/m	D 256
unnotched 1/8 in (3.2 mm) section	22.0 ft-lbs/in	1175 J/m	D 4812
Tensile Strength	4200 psi	29 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.22 x 10 ⁶ psi	1517 MPa	D 638
Flexural Strength	5300 psi	37 MPa	D 790
Flexural Modulus	0.18 x 10 ⁶ psi	1241 MPa	D 790
ELECTRICAL			
Dielectric Strength, S/T, in oil	500 VPM	19.7 kV/mm	D 149
THERMAL			
Deflection Temperature @ 264 psi (1820 kPa)	130 °F	54 °C	D 648
Ignition Resistance* Flammability**	V-2 @ 1/32 in	V-2 @ 0.8 mm	D 3801

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C