



**Product Data Sheet &
General Processing Conditions**

**RTP 4000 AF-1550 V0
Polyphthalamide (PPA)
Glass Fiber
Mineral
Flame Retardant**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.81	1.81	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0020 - 0.0030 in/in	0.20 - 0.30 %	D 955
Water Absorption, 24 hrs @ 23°C	0.100 %	0.100 %	D 570

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.7 ft-lbs/in	37 J/m	D 256
unnotched 1/8 in (3.2 mm) section	7.0 ft-lbs/in	374 J/m	D 4812
Tensile Strength	18500 psi	128 MPa	D 638
Tensile Elongation	1.0 - 2.0 %	1.0 - 2.0 %	D 638
Tensile Modulus	2.30 x 10 ⁶ psi	15858 MPa	D 638
Flexural Strength	28500 psi	197 MPa	D 790
Flexural Modulus	2.10 x 10 ⁶ psi	14480 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	250 °F	121 °C	D 648
@ 66 psi (455 kPa)	260 °F	127 °C	D 648
Ignition Resistance*			
Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	575 - 625 °F	302 - 329 °C
Mold Temperature	275 - 325 °F	135 - 163 °C
Drying	4 - 6 hrs @ 225 °F	4 - 6 hrs @ 107 °C
Moisture Content	0.05 %	0.05 %
Dew Point	-25 °F	-32 °C

PROCESSING NOTES

Desiccant Type Dryer Required.