

(+) 18816996168

Poncioplastics.com



**Product Data Sheet &
General Processing Conditions**

**RTP 4082
Polyphthalamide (PPA)
Carbon Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	15 %	15 %	
Specific Gravity	1.27	1.27	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0010 - 0.0030 in/in	0.10 - 0.30 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.8 ft-lbs/in	43 J/m	D 256
unnotched 1/8 in (3.2 mm) section	9.0 ft-lbs/in	481 J/m	D 4812
Tensile Strength	30000 psi	207 MPa	D 638
Tensile Elongation	1.0 - 2.0 %	1.0 - 2.0 %	D 638
Tensile Modulus	2.00 x 10 ⁶ psi	13790 MPa	D 638
Flexural Strength	44000 psi	303 MPa	D 790
Flexural Modulus	1.80 x 10 ⁶ psi	12411 MPa	D 790

ELECTRICAL

Volume Resistivity	< 1E6 ohm.cm	< 1E6 ohm.cm	D 257
--------------------	--------------	--------------	-------

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	510 °F	266 °C	D 648
Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	575 - 625 °F	302 - 329 °C
Mold Temperature	275 - 325 °F	135 - 163 °C
Drying	4 - 6 hrs @ 225 °F	4 - 6 hrs @ 107 °C
Moisture Content	0.05 %	0.05 %
Dew Point	-25 °F	-32 °C

PROCESSING NOTES

Desiccant Type Dryer Required.