

(+) 18816996168

Ponciplastics.com



Product Data Sheet & General Processing Conditions

RTP 1305 TFE 13 SI 2 Polyphenylene Sulfide (PPS) Glass Fiber Reinforced PTFE & Silicone Lubricated

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	30 %	30 %	
Specific Gravity	1.66	1.66	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0020 in/in	0.20 %	D 955

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	1.4 ft-lbs/in	75 J/m	D 256
unnotched 1/8 in (3.2 mm) section	7.0 ft-lbs/in	374 J/m	D 4812
Tensile Strength	19000 psi	131 MPa	D 638
Tensile Elongation	1.0 - 2.0 %	1.0 - 2.0 %	D 638
Tensile Modulus	1.70 x 10 ⁶ psi	11722 MPa	D 638
Flexural Strength	29000 psi	200 MPa	D 790
Flexural Modulus	1.65 x 10 ⁶ psi	11377 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	500 °F	260 °C	D 648
Ignition Resistance*			
Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	585 - 625 °F	307 - 329 °C
Mold Temperature	275 - 350 °F	135 - 177 °C
Drying	6 hrs @ 300 °F	6 hrs @ 149 °C
Moisture Content	0.04 %	0.04 %