



**Product Data Sheet &
General Processing Conditions**

**RTP 2300 A FR
Rigid Thermoplastic Polyurethane
(RTPU)
Flame Retardant**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.37	1.37	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0050 - 0.0070 in/in	0.50 - 0.70 %	D 955
Water Absorption, 24 hrs @ 23°C	0.150 %	0.150 %	D 570

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	4.0 ft-lbs/in	214 J/m	D 256
unnotched 1/8 in (3.2 mm) section	30.0 ft-lbs/in	1602 J/m	D 4812
Tensile Strength	6000 psi	41 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.28 x 10 ⁶ psi	1931 MPa	D 638
Flexural Strength	10000 psi	69 MPa	D 790
Flexural Modulus	0.30 x 10 ⁶ psi	2068 MPa	D 790

THERMAL

Ignition Resistance* Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801
--	---------------	--------------	--------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	430 - 470 °F	221 - 243 °C
Mold Temperature	125 - 200 °F	52 - 93 °C
Drying	4 - 6 hrs @ 225 °F	4 - 6 hrs @ 107 °C
Moisture Content	0.01 %	0.01 %
Dew Point	-40 °F	-40 °C

PROCESSING NOTES

Desiccant Type Dryer Required.