

(+) 18816996168

Ponciplastics.com



**Product Data Sheet &
General Processing Conditions**

**RTP 2740 S-30A
Saturated Styrenic Block Copolymer
(TES/SEBS or other)
General Purpose**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.08	1.08	D 792
MECHANICAL			
Tensile Strength Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	550 psi	4 MPa	D 412
Tensile Elongation Break, Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	700.0 %	700.0 %	D 412
Tensile Stress @ 100 %	100.0 psi	0.7 MPa	D 412
Tear Strength, Die C	90.0 pli	15.8 N/mm	D 624
Compression Set 22 h @ 23 °C (73 °F), Method B, Type 2	11 %	11 %	D 395
22 h @ 70 °C (158 °F), Method B, Type 2	37 %	37 %	D 395
Hardness Shore A, 10 s delay	30	30	D 2240
THERMAL			
Ignition Resistance*			
Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	5000 - 10000 psi	34 - 69 MPa
Melt Temperature	325 - 400 °F	163 - 204 °C
Mold Temperature	60 - 100 °F	16 - 38 °C
Drying	2 - 4 hrs @ 160 °F	2 - 4 hrs @ 71 °C
Moisture Content	0.04 %	0.04 %