

(+) 18816996168

Poncioplastics.com



**Product Data Sheet &
General Processing Conditions**

**RTP 1505-55D
Polyether-Ester Block Copolymer
(TEEE/COPE)
Glass Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	30 %	30 %	
Specific Gravity	1.42	1.42	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0015 - 0.0021 in/in	0.15 - 0.21 %	D 955
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	6.7 ft-lbs/in	358 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	7350 psi	51 MPa	D 638
Tensile Elongation	9.2 %	9.2 %	D 638
Tensile Modulus	0.36 x 10 ⁶ psi	2482 MPa	D 638
Flexural Strength	10200 psi	70 MPa	D 790
Flexural Modulus	0.34 x 10 ⁶ psi	2344 MPa	D 790
Hardness Shore D, instantaneous	65	65	D 2240

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	410 - 460 °F	210 - 238 °C
Mold Temperature	70 - 100 °F	21 - 38 °C
Drying	2 - 4 hrs @ 220 °F	2 - 4 hrs @ 104 °C
Moisture Content	< 0.10 %	< 0.10 %

PROCESSING NOTES

Desiccant Type Dryer Required.