



**Product Data Sheet &
General Processing Conditions**

**Polabond® 6003-45A
Speciality Thermoplastic Elastomer
PC/PMMA, PC/PBT bondable**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.96	0.96	D 792
MECHANICAL			
Tensile Strength Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	780 psi	5 MPa	D 412
Tensile Elongation Break, Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	630.0 %	630.0 %	D 412
Tensile Stress Die C 0.125 in, 20 in/min (3.2 mm, 500 mm/min) @ 100 %	220.0 psi	1.5 MPa	D 412
Tear Strength, Die C	140.0 pli	24.5 N/mm	D 624
Peel Strength *** 90 degrees, 20 in/min (500 mm/min) PC/PMMA, Failure Type D PC/PBT, Failure Type D	24.0 pli 20.0 pli	4.2 N/mm 3.5 N/mm	RTP 55 RTP 55
Compression Set 22 h @ 23 °C (73 °F), Method B, Type 2 22 h @ 70 °C (158 °F), Method B, Type 2	16 % 66 %	16 % 66 %	D 395 D 395
Hardness Shore A, 10 s delay	45	45	D 2240
THERMAL			
Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

*** Values per RTP Company testing. Failure types: R=overmold failure, D=interface failure, S=substrate failure.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Melt Temperature	380 - 460 °F	193 - 238 °C
Mold Temperature	70 - 120 °F	21 - 49 °C
Drying	2 - 4 hrs @ 180 °F	2 - 4 hrs @ 82 °C
Moisture Content	< 0.03 %	< 0.03 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.