

Reny™ G-16S

Mitsubishi Engineering-Plastics Corp - High Performance Polyamide

General Information				
Product Description				
Carbon Fiber-reinforced; Abrasion Resistant; HB equivalent per in-house testing				
General				
Filler / Reinforcement	• Carbon Fiber, 20% Filler by Weight			
Features	• Abrasion Resistant			
Uses	• Automotive Applications • Automotive Electronics		• Electrical/Electronic Applications • General Purpose	
ASTM & ISO Properties ¹				
Physical	Dry	Conditioned	Unit	Test Method
Density	1.43	--	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR)				ISO 1133
275°C/2.16 kg	8.8	--	g/10 min	
Melt Volume-Flow Rate (MVR)				ISO 1133
275°C/2.16 kg	6.1	--	cm³/10min	
Molding Shrinkage ²				Internal Method
Across Flow : 130°C, 2.00 mm	0.51	--	%	
Flow : 130°C, 2.00 mm	0.18	--	%	
Water Absorption				Internal Method
24 hr, 23°C	0.12	--	%	
Equilibrium, 23°C, 50% RH	1.1	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	20200	19900	MPa	ISO 527-1/1
Tensile Stress (Break)	230	205	MPa	ISO 527-2/5
Tensile Strain (Break)	1.6	1.6	%	ISO 527-2/5
Flexural Modulus ³	18800	18200	MPa	ISO 178
Flexural Stress ³	338	294	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
23°C	4.4	4.5	kJ/m²	
Charpy Unnotched Impact Strength				ISO 179
23°C	50	39	kJ/m²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2/A
1.8 MPa, Unannealed	240	234	°C	
Additional Information				
Conditioned	Conditioned to 50% RH			

(+) 18816996168

Ponciplastics.com

Reny™ G-16S

Mitsubishi Engineering-Plastics Corp - High Performance Polyamide

Processing Information		
Injection	Dry	Unit
Drying Temperature		
Hot Air Dryer, A	120	°C
Hot Air Dryer, B	80	°C
Drying Time		
Hot Air Dryer, A	> 3.0	hr
Hot Air Dryer, B	> 12	hr
Rear Temperature	270	°C
Middle Temperature	275	°C
Front Temperature	280	°C
Nozzle Temperature	280	°C
Mold Temperature	120 to 140	°C
Injection Pressure	20.0 to 150	MPa
Injection Rate	Moderate-Fast	
Screw Speed	60 to 150	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² 100-mm square

³ 2.0 mm/min

(+) 18816996168

Poncioplastics.com