

NOVADURAN™ 5810N2 1

Mitsubishi Engineering-Plastics Corp - Polybutylene Terephthalate

General Information

Product Description

Un-reinforced / V-0 (1.5 mm) equivalent per in-house testing, Low Warpage, Low Density

General

Features	• Flame Retardant • Low Density • Low Warpage
Uses	• Automotive Applications • Electrical/Electronic Applications • Automotive Electronics • General Purpose

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.34	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	15	cm ³ /10min	ISO 1133
Water Absorption (Saturation, 23°C)	0.080	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	50.0	MPa	ISO 527-2/50
Tensile Strain (Break)	10	%	ISO 527-2/50
Flexural Modulus ²	2600	MPa	ISO 178
Flexural Stress ²	83.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Annealed	131	°C	ISO 75-2/B
1.8 MPa, Annealed	83.0	°C	ISO 75-2/A

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	120	°C
Drying Time - Hot Air Dryer	5.0 to 8.0	hr
Rear Temperature	240 to 260	°C
Middle Temperature	240 to 260	°C
Front Temperature	240 to 260	°C
Nozzle Temperature	260	°C
Mold Temperature	60 to 100	°C
Injection Pressure	20.0 to 150	MPa
Injection Rate	Moderate-Fast	
Screw Speed	80 to 120	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 mm/min

(+) 18816996168

Ponciplastics.com