

Iupital™ FU2050

Mitsubishi Engineering-Plastics Corp - Acetal (POM) Copolymer

General Information

Product Description

Impact Resistance; High

General

Features	- High Impact Resistance - Soft
Uses	- Automotive Applications - Electrical/Electronic Applications - Automotive Electronics - General Purpose

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.29	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.5	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	3.9	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.00 mm)	1.2	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	800	MPa	ISO 527-1/1
Tensile Stress (Yield)	24.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	20	%	
Break	> 200	%	
Flexural Modulus ²	750	MPa	ISO 178
Flexural Stress ²	24.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	65	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/A
1.8 MPa, Unannealed	64.0	°C	
Melting Temperature	166	°C	ISO 11357-3
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	80	°C
Drying Time - Hot Air Dryer	3.0 to 4.0	hr
Rear Temperature	170	°C
Middle Temperature	180	°C
Front Temperature	190	°C
Nozzle Temperature	180 to 210	°C

(+) 18816996168

Ponciplastics.com

Iupital™ FU2050

Mitsubishi Engineering-Plastics Corp - Acetal (POM) Copolymer

Injection	Nominal Value	Unit
Mold Temperature	< 40	°C
Injection Pressure	50.0 to 100	MPa
Injection Rate	Moderate	
Screw Speed	80 to 120	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 mm/min

(+) 18816996168

Ponciplastics.com